

STONE SPECIFICATION

Gosford Buff



HOW TO SPECIFY

GENERAL:	Sandstone shall be Gosford Buff Sandstone by Gosford Quarries.
STONE TYPE:	Gosford Buff Sandstone
COLOUR:	Grey-buff with a fine black speckle / spot.
STONE FINISH:	Diamond sawn, Gang sawn, Honed, Rockfaced, Sparrow pecked & Custom
SIZES:	As specified by architect
FIXING:	Adhesive Material to be compatible to substrate medium. Stone cladding above 2.3 metres in height to be mechanically fixed. Refer to ASAA Natural Stone Design manual for more information.
SEALING:	Sealer to be specified by designer or installer

TYPICAL TECHNICAL SPECIFICATION

BULK DENSITY (ASTM C97-83):	2.23 tonnes/m ³
ABSORPTION BY WEIGHT (ASTM C97-83):	5.0 %
MODULUS OF RUPTURE:	8.0 MPa Dry, 2.5 MPa Wet
COMPRESSIVE STRENGTH (ASTM C170-87):	50 MPa Dry, 25 MPa Wet



*Sandstone is a natural product and therefore subject to variation in colour, tone, shade and texture.

TERREY HILLS SHOWROOM

301 Mona Vale Road
Terrey Hills NSW 2084
P 02 8585 8282

SOMERSBY SHOWROOM

70 Quarry Rd
Somersby NSW 2250
P 02 4340 3000

CLAYTON SOUTH SHOWROOM

9 Prestige Drive
Clayton South VIC 3169
P 03 9558 2283

BEAUDESERT SHOWROOM

1812 Beaudesert Boonah Rd,
Allenvue QLD 4285
P 07 5541 0143



facebook.com/SandstoneAustralia/



www.gosfordquarries.com.au



instagram.com/gosfordquarries/