

STONE SPECIFICATION

Wondabyne



HOW TO SPECIFY

GENERAL:	Sandstone shall be Wondabyne Sandstone by Gosford Quarries
STONE TYPE:	Wondabyne Sandstone
COLOUR:	Grey - Buff
STONE FINISH:	Diamond sawn, Gang sawn, Honed, Rockfaced, Sparrow pecked & Custom
SIZES:	As specified by architect
FIXING:	Adhesive Material to be compatible to substrate medium. Stone cladding above 2.3 metres in height to be mechanically fixed. Refer to ASAA Natural Stone Design manual for more information.
SEALING:	Sealer to be specified by designer or installer

TYPICAL TECHNICAL SPECIFICATION

BULK DENSITY (ASTM C97-83):	2.28 tonnes/m ³
ABSORPTION BY WEIGHT (ASTM C97-83):	3.75%
MODULUS OF RUPTURE:	8.5 MPa Dry, 3.5 MPa Wet
COMPRESSIVE STRENGTH (ASTM C170-87):	57 MPa Dry, 30 MPa Wet



**GOSFORD
QUARRIES
SANDSTONE**

*Sandstone is a natural product and therefore subject to variation in colour, tone, shade and texture.

TERREY HILLS SHOWROOM

301 Mona Vale Road
Terrey Hills NSW 2084
P 02 8585 8282

SOMERSBY SHOWROOM

70 Quarry Rd
Somersby NSW 2250
P 02 4340 3000

CLAYTON SOUTH SHOWROOM

9 Prestige Drive
Clayton South VIC 3169
P 03 9558 2283

BEAUDESERT SHOWROOM

1812 Beaudesert Boonah Rd,
Allenvue QLD 4285
P 07 5541 0143



facebook.com/SandstoneAustralia/



www.gosfordquarries.com.au



instagram.com/gosfordquarries/