

# PC CREAM SPECIFICATION SHEET



## HOW TO SPECIFY

**GENERAL** SANDSTONE FROM GOSFORD QUARRIES PTY LTD

**STONE COLOUR** CREAM SANDSTONE (OXIDISING)

**QUARRY SOURCE** PILES CREEK QUARRY, NSW

**SIZES** AVAILABLE IN STANDARD AND CUSTOM SIZES & FINISHES

*Results for natural stone will vary, all results are indicative. Contact us for more information.*

## TECHNICAL SPECS

**BULK DENSITY**  
(ASTM C97 -83): 2.216 TONNES/M<sup>3</sup>

**ABSORPTION BY WEIGHT**  
(ASTM C97 -83): 4.2%

**MODULUS OF RUPTURE**  
7.3MPA DRY, 3.2MPA WET

**COMPRESSIVE STRENGTH**  
(ASTM C170 -87): 75MPa Dry, 45MPa Wet