


GUINEA GOLD SPECIFICATION SHEET



HOW TO SPECIFY

GENERAL SANDSTONE FROM GOSFORD QUARRIES PTY LTD

STONE COLOUR GUINEA GOLD SANDSTONE (OXIDISING)

QUARRY SOURCE PILES CREEK QUARRY, NSW

SIZES AVAILABLE IN STANDARD AND CUSTOM SIZES & FINISHES

Results for natural stone will vary, all results are indicative. Contact us for more information.

TECHNICAL SPECS

BULK DENSITY
(ASTM C97 -83): 2.226 TONNES/M³

ABSORPTION BY WEIGHT
(ASTM C97 -83): 4.4%

MODULUS OF RUPTURE
6.5MPA DRY, 3.6MPA WET

COMPRESSIVE STRENGTH
(ASTM C170 -87): 69MPa Dry, 47MPa Wet

RESISTANCE TO SALT ATTACK
0.7% LOSS (A GRADE)