

— QUARRY RUN SPECIFICATION SHEET



HOW TO SPECIFY

GENERAL SANDSTONE FROM GOSFORD QUARRIES PTY LTD

STONE COLOUR QUARRY RUN (NON-SELECT) SANDSTONE

QUARRY SOURCE N/A

SIZES AVAILABLE IN STANDARD AND CUSTOM SIZES & FINISHES

Contact us for more information on sizes and textures available 02 8585 8282

TECHNICAL SPECS

BULK DENSITY
(ASTM C97 -83): 2.262 TONNES/M³

ABSORPTION BY WEIGHT
(ASTM C97 -83): 4.2%

MODULUS OF RUPTURE
7.6MPA DRY, 2.6MPA WET

COMPRESSIVE STRENGTH
(ASTM C170 -87): 69MPa Dry, 37MPa Wet

Results for natural stone will vary, all results are indicative