

— WONDABYNE SPECIFICATION SHEET



HOW TO SPECIFY

GENERAL SANDSTONE FROM GOSFORD QUARRIES PTY LTD

STONE COLOUR WONDABYNE SANDSTONE

QUARRY SOURCE WONDABYNE QUARRY, NSW

SIZES AVAILABLE IN STANDARD AND CUSTOM SIZES & FINISHES

Results for natural stone will vary, all results are indicative. Contact us for more information.

TECHNICAL SPECS

BULK DENSITY
(ASTM C97 -83): 2.308 TONNES/M³

ABSORPTION BY WEIGHT
(ASTM C97 -83): 3.4%

MODULUS OF RUPTURE
6.2MPA DRY, 2.8MPA WET

COMPRESSIVE STRENGTH
(ASTM C170 -87): 75MPa Dry, 41MPa Wet

RESISTANCE TO SALT ATTACK
0.6% LOSS (A GRADE)